

PE 500

This grade exhibits a good combination of stiffness, toughness, mechanical damping ability with abrasion resistance, and it can easily be welded. In less demanding applications with respect to wear and impact resistance, PE 500 may present an economical alternative for the TIVAR standard grades. PE 500 is a versatile polyethylene grade used mainly in the food industry (meat and fish processing) but it is also put to use in all kinds of mechanical, chemical and electrical applications.

Physical properties (indicative values [■])

PROPERTIES	Test methods	Units	VALUES
Colour	-	-	natural (white)/green/black / colours
Average molar mass (average molecular weight) - (1)	-	10 ⁶ g/mol	0.5
Density	ISO 1183-1	g/cm ³	0.96
Water absorption at saturation in water of 23 °C (2)	-	%	0.01
Thermal Properties (3)			
Melting temperature (DSC, 10 °C/min)	ISO 11357-1/3	°C	135
Thermal conductivity at 23 °C	-	W/(K.m)	0.40
Average coefficient of linear thermal expansion between 23 and 100 °C	-	m/(m.K)	150 x 10 ⁻⁶
Temperature of deflection under load:			
- method A: 1.8 MPa	ISO 75-1/-2	°C	44
Vicat softening temperature - VST/B50	ISO 306	°C	80
Max. allowable service temperature in air:			
- for short periods (4)	-	°C	120
- continuously : for 20,000 h (5)	-	°C	80
Min. service temperature (6)	-	°C	-100
Flammability (7):			
- "Oxygen Index"	ISO 4589-1/-2	%	< 20
- according to UL 94 (6 mm thickness)	-	-	HB
Mechanical Properties at 23 °C (8)			
Tension test (9):			
- tensile stress at yield (10)	ISO 527-1/-2	MPa	28
- tensile strain at yield (10)	ISO 527-1/-2	%	10
- nominal tensile strain at break (10)	ISO 527-1/-2	%	> 50
- tensile modulus of elasticity (11)	ISO 527-1/-2	MPa	1300
Compression test (12):			
- compressive stress at 1 / 2 / 5 % nominal strain (11)	ISO 604	MPa	12 / 18.5 / 26.5
Flexure test (13)			
- flexural strength	ISO 178	MPa	27
Charpy impact strength - unnotched (14)	ISO 179-1/1eU	kJ/m ²	no break
Charpy impact strength - notched	ISO 179-1/1eA	kJ/m ²	105P
Charpy impact strength - notched (double 14° notch) - (15)	ISO 11542-2	kJ/m ²	25
Ball indentation hardness (16)	ISO 2039-1	N/mm ²	48
Shore hardness D (15 s) - (16)	ISO 2039-2	-	62
Relative weight loss during a wear test in "sand/water-slurry"; TIVAR 1000 = 100	ISO 15527	-	350
Electrical Properties at 23 °C			
Electric strength (17)	IEC 60243-1	kV/mm	45
Volume resistivity	IEC 60093	Ohm.cm	> 10 ¹⁴
Surface resistivity	IEC 60093	Ohm	> 10 ¹²
Relative permittivity ε _r :- at 100 Hz	IEC 60250	-	2.4
- at 1 MHz	IEC 60250	-	2.4
Dielectric dissipation factor tan δ: - at 100 Hz	IEC 60250	-	0.0002
- at 1 MHz	IEC 60250	-	0.0002
Comparative tracking index (CTI)	IEC 60112	-	600

Note: 1 g/cm³ = 1,000 kg/m³; 1 MPa = 1 N/mm²; 1 kV/mm = 1 MV/m.

Legend:

- (1) This is the average molar mass of the PE-HMW resins (irrespective of any additives) used for the manufacture of this material. It is calculated by means of the Margolies-equation $M = 5.37 \times 10^4 \times [\eta]^{1.49}$, with $[\eta]$ being the intrinsic viscosity (Staudinger index) derived from a viscosity measurement according to ISO-1628-3:2001, using decahydronaphthalene as a solvent (concentration of 0.001 g/cm³).
 - (2) Measured on 1 mm thick test specimens.
 - (3) The figures given for these properties are for the most part derived from raw material supplier data and other publications.
 - (4) Only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
 - (5) Temperature resistance over a period of 20,000 hours. After this period of time, there is a decrease in tensile strength – measured at 23 °C – of about 50 % as compared with the original value. The temperature value given here is thus based on the thermal-oxidative degradation which takes place and causes a reduction in properties. Note, however, that the maximum allowable service temperature depends in many cases essentially on the duration and the magnitude of the mechanical stresses to which the material is subjected.
 - (6) Impact strength decreasing with decreasing temperature, the minimum allowable service temperature is practically mainly determined by the extent to which the material is subjected to impact. The value given here is based on unfavourable impact conditions and may consequently not be considered as being the absolute practical limit.
 - (7) These estimated ratings, derived from raw material supplier data and other publications, are not intended to reflect hazards presented by the material under actual fire conditions. There is no 'UL File Number' available for PE 500 stock shapes.
 - (8) The figures given for these properties are average values of tests run on test specimens machined out of 30 mm thick plates.
 - (9) Test specimens: Type 1 B
 - (10) Test speed: 50 mm/min
 - (11) Test speed: 1 mm/min.
 - (12) Test specimens: cylinders Ø 8 x 16 mm
 - (13) Test specimens: bars 4 (thickness) x 10 x 80 mm ; test speed: 2 mm/min ; span: 64 mm.
 - (14) Pendulum used: 15 J
 - (15) Pendulum used: 25 J
 - (16) Measured on 10 mm thick test specimens.
 - (17) Electrode configuration: Ø 25 / Ø 75 mm coaxial cylinders ; in transformer oil according to IEC 60296 ; 1 mm thick test specimens. Please note that the electric strength of PE 500 **black** can be considerably lower than the figure listed in the table which refers to natural material.
- This table is a valuable help in the choice of a material. The data listed here fall within the normal range of product properties. However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.

AVAILABILITY

Round Rods: Ø 30-200 mm - **Plates:** Thicknesses 8-140 mm

All information supplied by or on behalf of Quadrant Engineering Plastic Products in relation to its products, in any form, is supported by research and believed to be reliable, but Quadrant Engineering Plastic Products assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Quadrant Engineering Plastic Products for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.